



Manufacturer's Product Specification

Scope

This specification sheet covers the manufacturer's requirements for PVC and CPVC tubes in accordance with respective international standards. These tubes meet or exceed the standards set by the American Society for Testing and Materials, the National Sanitation Foundation, British Standards Institute, German Industrial Norms and Japanese Industrial Standards.

Dimensions and Wall Thicknesses

Physical dimensions, wall thickness and tolerances of PVC and CPVC tubes meet the requirements of ASTM, DIN and BS specifications for tubes.

PVC and CPVC Materials

Rigid PVC (polyvinyl chloride) and CPVC (chlorinated polyvinyl chloride) used in the manufacture of tubes is Type I, Grade 1 PVC compound, and Type IV, Grade 1 CPVC compound as stated in ASTM D-1784. Raw material used in extrusion shall contain the specified amounts of color pigment, stabilizers, and other additives approved by the National Sanitation Foundation.

Marking

PVC and CPVC tubes are marked as prescribed in ASTM D-1784 to indicate the manufacturer's name or trademark, size of Tube, material designation, batch number and month of production. There must be clear distinguishing on those products that are PVC and those products that are CPVC. Where there is no restriction of space, wall thicknesses shall also be indicated.

PVC TUBE PHYSICAL PROPERTIES

GENERAL	VALUE	TEST METHOD
Cell Classification	12454	ASTM D1784
Maximum Service Temp.	140°F	
Color	White, Dark Gray	
Specific Gravity, (g/cu.cm @ 73°F)	1.40 +/-02	ASTM D792
Water Absorption % increase 24 hrs @ 25°C	0.05	ASTM D570
Hardness, Rockwell	110 - 120	ASTM D785
Poisson's Ratio @ 73°F	0.410	
Hazen-Williams Factor	C =150	
MECHANICAL		
Tensile Strength, psi @ 73°F	7,450	ASTM D638
Tensile Modulus of Elasticity, psi @ 73°F	420,000	ASTM D638
Flexural Strength, psi @ 73°F	14,450	ASTM D790
Flexural Modulus, psi @ 73°F	360,000	ASTM D790
Compressive Strength, psi @ 73°F	9,600	ASTM D695
Izod Impact, notched, ft-lb/in @ 73°F	0.75	ASTM D256
THERMAL		
Coefficient of Linear Expansion (in/in/°F)	2.9×10^{-5}	ASTM D696
Coefficient of Thermal Conductivity (Cal.)(cm)/(cm ²)(Sec.)(°C) BTU/in/hr/ft.2/°F Watt/m ² /K	3.5×10^{-4} 1.02 0.147	ASTM C177
Heat Deflection Temperature Under Load (264 psi, annealed)	170	ASTM D648
Specific Heat, Cal./°C/gm	0.25	ASTM D2766
ELECTRICAL		
Dielectric Strength, volts/mil	1,413	ASTM D149
Dielectric Constant, 60Hz, 30°F	3.70	ASTM D150
Volume Resistivity, ohm/cm @ 95°C	1.2×10^{12}	ASTM D257
Harvel PVC tube is non-electrolytic		
FIRE PERFORMANCE		
Flammability Rating	V-0	UL-94
Flame Spread Index	<10	
Flame Spread	0-25	ULC
Smoke Generation	80-225	ULC
Flash Ignition Temp.	730°F	
Average Time of Burning (sec.)	<5	ASTM D635
Average Extent of Burning (mm)	<10	
Burning Rate (in/min)	Self Extinguishing	
Softening Starts (approx.)	250°F	
Material Becomes Viscous	350°F	
Material Carbonizes	425°F	
Limiting Oxygen Index (LOI)	43	ASTM D2863
Clean Room Materials Flammability Test	N/A	FM 4910

Note: The physical properties shown are considered general PVC physical properties. HYDROSEAL utilizes several PVC compounds for the production of different PVC product lines. PVC compounds may exhibit slight variations in actual physical properties as compared to those stated. Contact your HYDROSEAL representative for additional information if necessary

Notes: PVC/CPVC material meets ASTM Standard D-1784
Dimensions are subject to change without notice. Contact your HYDROSEAL representative for certification.

PVC ASTM D-1785 SCHEDULE 40

PART	NOMINAL SIZE	OUTSIDE DIAMETER		CLEAR PVC SCHEDULE 40			
				WALL THICKNESS		WORKING PRESSURE	WEIGHT
				IN	MM	IN	MM
0200.40K.0050	1/2"	0.84	21.34	0.109	2.77	600	0.14
0200.40K.0075	3/4"	1.05	26.67	0.113	2.87	480	0.18
0200.40K.0100	1"	1.32	33.40	0.133	3.38	450	0.27
0200.40K.0125	1 1/4"	1.66	42.16	0.140	3.56	370	0.36
0200.40K.0150	1 1/2"	1.90	48.26	0.145	3.68	330	0.43
0200.40K.0200	2"	2.38	60.33	0.154	3.91	280	0.58
0200.40K.0250	2 1/2"	2.88	73.03	0.203	5.16	300	0.91
0200.40K.0300	3"	3.50	88.90	0.216	5.49	260	1.19
0200.40K.0400	4"	4.50	114.30	0.237	6.02	220	1.69
0200.40K.0600	6"	6.63	168.28	0.280	7.11	180	2.99

PVC WTF™ Series CONTAINMENT PLUS

PART	NOMINAL SIZE	OUTSIDE DIAMETER		WTF™ Series CONTAINMENT PLUS			
				WALL THICKNESS		WORKING PRESSURE	WEIGHT
				IN	MM	IN	MM
0200.WTK.0050	1/2"	0.84	21.34	0.091	2.30	525	0.11
0200.WTK.0075	3/4"	1.05	26.67	0.091	2.30	400	0.14
0200.WTK.0100	1"	1.32	33.40	0.102	2.60	360	0.21
0200.WTK.0125	1 1/4"	1.66	42.16	0.118	3.00	320	0.30
0200.WTK.0150	1 1/2"	1.90	48.26	0.122	3.10	290	0.36
0200.WTK.0200	2"	2.38	60.33	0.138	3.50	250	0.52
0200.WTK.0250	2 1/2"	2.88	73.03	0.161	4.10	250	0.72
0200.WTK.0300	3"	3.50	88.90	0.193	4.90	240	1.06
0200.WTK.0400	4"	4.50	114.30	0.205	5.20	200	1.46
0200.WTK.0600	6"	6.63	168.28	0.268	6.80	170	2.86

DERATING FACTOR

PVC	
TEMP(C)	FACTOR
73	1.00
80	0.88
90	0.75
100	0.62
110	0.51
120	0.40
130	0.31
140	0.22